



Properties	Values
Transmission Range	1.0 to 13 μm
Refractive Index	2.192 at 10.6 μm
Reflection Loss	24.6% at 10.6 μm
Absorption Coefficient	0.02 cm ⁻¹ at 3.8 μm
Reststrahlen Peak	30.5 μm
dn/dT	+43 x 10 ⁻⁶ /°C at 3.39 μm
dn/dμ = 0	n/a
Density	4.08 g/cc